

A Comprehensive Systematic Review on the Application of Coal Ash in Bituminous Pavements

Sagar Kailas Sonawane^{1,4}, Dr. Arun Kumar Dwivedi², Dr. Premanand
L. Naktode³

¹Research Scholar, Department of Civil Engineering, School of Engineering and
Technology, Sandip University, Nashik, Maharashtra, India

²Professor, Department of Civil Engineering, School of Engineering and Technology,
Sandip University, Nashik, Maharashtra, India

³Principal, Tulsiramji Gaikwad-Patil College of Engineering & Technology, Wardha
Road, Nagpur, Maharashtra, India

⁴School of Engineering and Sciences, MIT Art, Design & Technology University, Pune,
Maharashtra, India

Email: sagar17793@gmail.com

The application of coal ash in bituminous mixes has gained significant attention in recent years due to its potential to enhance the physical & mechanical properties of asphalt mixes, which reduce construction costs and promote sustainable waste management practices. This comprehensive systematic review summarizes current research on the utilization of different types of coal ash like fly ash, bottom ash, cenospheres and boiler slag in the bituminous mixtures. The review examines the effects of coal ash on the performance of bituminous pavements like stability, durability, moisture resistance, environmental impact and cost-benefit analysis of coal ash modified mixes. Additionally, the review explores the challenges associated with coal ash usage such as variability in composition and regulatory concerns. The results from various literatures show that the application of coal ash in bituminous mixes improves Marshall parameters like stability, flow value, and resistance to rutting, with additions of up to 2-3% by volume of the mix. Further additions of 4-5% enhance resistance to moisture damage and fatigue cracking. Additionally, utilizing coal ash in bituminous mixes can lead to a 12% savings in natural material costs. Overall, the findings suggest that coal ash when appropriately processed, analyzed and utilized, can serve as a feasible alternative to conventional materials in bituminous pavement construction contributing to both economic and environmental sustainability.

Keywords: Coal ash, Fly ash, Bottom ash, Bituminous mixes, Stability, Durability, Rutting, Moisture resistance, Sustainability.

1. Introduction

The rapid industrial development and increased energy demand of the modern world have led to the generation of huge quantities of coal combustion byproducts, particularly coal ash.

Traditionally considered an industrial waste requiring safe disposal, coal ash has recently emerged as a most prominent resource in various construction applications, particularly in the production of bituminous mixtures used in road construction. The utilization of fly ash constitutes merely one-quarter of its overall generation. Leading producers such as India and China exhibit a utilization rate below 50%, whereas countries like Denmark, Italy and the Netherlands achieve a fly ash utilization rate of 100% [1]. The utilization of coal ash into bituminous mixtures offers a dual benefit; it addresses the environmental challenges associated with coal ash disposal while simultaneously enhancing the performance characteristics of bituminous pavements.

Bituminous mixtures commonly known as asphalt which are important material in road construction providing durable & flexible surfaces that withstand the traffic loads and environmental conditions. However, the increasing cost and scarcity of conventional materials such as natural aggregates and fillers have driven the search for alternative sustainable materials. Coal ash with its pozzolanic properties and fine particle size, has shown promise as an additive or partial replacement for traditional materials in bituminous mixture production.

This systematic review aims to provide a comprehensive analysis of the existing literature on the application of coal ash in bituminous mixtures. By examining the various types of coal ash, their impact on the mechanical and environmental performance of bituminous mixes and the challenges & opportunities associated with their use, this review seeks to offer insights into the potential of coal ash use as a sustainable material in road paving sector. Through this review, the main aim is to identify key trends, gaps in knowledge and future research directions to further advance the understanding and application of coal ash in bituminous pavements.

2. Coal ash types and their characteristics

Coal ash is a mineral byproduct of coal combustion in thermal power plants and is available in various forms, each with distinct physical and chemical properties that affect its suitability for use in bituminous mixtures. The byproduct of the combustion process in the absence of SO₂ mitigation particularly involving pulverized coal is consists of bottom ash, fly ash and boiler slag. The common elements found in coal ash are sodium, calcium, magnesium, potassium, aluminum, silicon, iron and sulfur [2]. This section provides a detailed analysis of the different coal ash types focusing on their characteristics and important applications in bituminous mixes production.

2.1 Fly ash

Fly ash is the most significantly studied as well as utilized type of coal ash in bituminous mixes. It is collected from the flue gases of thermal-power plants by using electrostatic precipitators or filter bags. The fly ash mainly consists of fine, shiny spheres usually less than 100 microns in diameter accompanied by coarser crystalline substances & differing percentage of unburned carbon particulate matter. This small particle size distribution enhances the workability as well as compactability of bituminous mixes [3, 4]. Fly ash collected from the flue gases amounts to approximately 75-85% of the aggregate particulate matter that exits the combustion chamber during burning [5, 6]. The chemical composition of fly ash generally has high contents of silica (SiO₂), alumina (Al₂O₃), iron oxide (Fe₂O₃) and calcium oxide making

it an ASTM class F pozzolanic material [7, 8]. As per the ASTM C618-22 standards [9, 10] fly ash is broadly categorized into two classes based on its chemical composition, unburned carbon content and particle sizes. Class C known as ‘high lime’ ash, which has certain self-hardening characteristics is mostly located in the western region of the United States, while the Class F known as ‘low lime’ ash, which functions as a pozzolan which is largely found in the eastern part of the United States. The types of fly ash as per IS 3812-1 [11] are Grade I which is derived from bituminous coal having fractions ($\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$) greater than 70% and Grade II which is derived from lignite coal having fractions ($\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$) greater than 50%. As per the X-ray fluorescence (XRF) test conducted by Khairul Nizar Ismail et al. [12], the physical properties of fly ash sample are shown in table 1. Also, the optimum moisture content (OMC) values for fly ashes varies from 11 to 53% and maximum dry density values ranges from 1.01 to 1.78 g/cm^3 [1]. The table 2 shows the chemical composition ranges of fly ash generally the samples from India, China, Italy, Denmark, Netherlands, United States and Europe. From table 2, it seems that the silica dioxide concentration in the fly ash produced in India (ranging from 50% to 60%) is significantly greater than that observed in the fly ash from both China and the United States (which ranges from 36% to 38%, reaching up to 57% to 58%). The Al_2O_3 content range is comparatively wider for China than for other countries listed in table 2, while for the Netherlands the range is the narrowest. The pozzolanic properties of fly ash enhance the long-term strength and durability of asphalt pavements by decreasing the permeability and increases the resistance to moisture-induced damage [7, 13]. The fly ash can replace a small portion of the fine aggregates or fillers in bituminous mixes leading to overall cost savings and enhanced performance [3, 4].

Table 1 Physical properties of fly ash [12]

Sr. No.	Physical property	Results
1	Color	Whitish grey
2	Average particle size (μm)	6.92
3	Moisture content (%)	3.14
4	Bulk density (g/cm^3)	0.994
5	Specific gravity	2.288

Table 2 Chemical composition ranges of fly ash samples from various countries

Sr. No.	Chemical composition (%)	Country						
		India [14-16]	China [15]	Italy [17, 18]	Denmark [19]	Netherlands [17, 20]	United States [15, 21, 22]	Europe [15]
1	SiO_2	50.2-59.7	35.6-57.2	41.7-54	48-65	45.1-59.7	34.9-58.5	28.5-59.7
2	Al_2O_3	14-32.4	18.8-55	25.9-33.4	26-33	24.8-28.9	19.1-28.6	12.5-35.6
3	Fe_2O_3	2.7-16.6	2.3-19.3	3-8.8	3.3-8.3	3.3-9	3.2-25.5	2.6-21.2
4	CaO	0.6-9	1.1-7	2-10	2.2-7.8	0.5-6.8	0.7-22.4	0.5-28.9
5	MgO	0.1-2.3	0.7-4.8	0-2.4	na	0.6-3.7	0.5-4.8	0.6-3.8
6	K_2O	0.2-4.7	0.8-0.9	0-2.6	na	0.6-2.9	0.9-2.9	0.4-4
7	SO_3	na	1-2.9	na	na	0.2-1.3	0.1-2.1	0.1-12.7
8	TiO_2	0.3-2.7	0.2-0.7	1-2.6	na	0.9-1.8	1-1.6	0.5-2.6

9	Na ₂ O	0.2-1.2	0.6-1.3	0-1	1.1-2.8	0.1-1.2	0.2-1.8	0.1-1.9
10	P ₂ O ₅	na	1.1-1.5	0-1.5	na	0.1-1.5	0.1-1.3	0.1-1.7
11	MnO	na	nf	0-0.1	na	0-0.1	na	0-0.2
12	LOI	0.5-7.2	nf	1.9-9	3.1-4.9	2.7-8.1	0.2-20.5	0.8-32.8

¹ note: na - not available and nf – not found.

2.2 Bottom ash

Bottom ash is a coarse and unevenly shaped granular material that settles at the bottom of coal furnaces. The size of bottom ash ranges between 50.8 mm & 0.075 mm [23]. It is less reactive than fly ash but holds usable properties that make it more suitable for applications in bituminous mixtures such as it has a sand like texture with a higher specific gravity compared to fly ash making bottom ash fit for using as a fine aggregate in asphalt mixes [13]. Like fly ash, bottom ash is also rich in silica, alumina and iron oxide contributing to its pozzolanic properties [7]. The physical properties of bottom ash obtained from three different sources are shown in table 3. Bottom ash has a moisture content of 0.43%. The fineness modulus values vary from 1.5 to 3.44, while its specific surface-area values ranges between 3835.75 and 10,500 cm²/g. The specific gravity values of bottom ash as per table 3 ranges between 1.39 and 2.41 whereas the water absorption coefficient values are between 6.8 and 32%. The chemical composition of bottom ash samples obtained from various coal-based power plants, where the chemical composition is expressed by the weight presented in table 4. From table 4 it is seen that silicon dioxide, aluminum oxide, and CaO are the primary mineral constituents in coal rock ash [24]. The porous nature of bottom ash allows for better drainage which can be advantageous in base and sub-base layers of road pavements, where its granular nature improves load distribution and provides cost-effective alternatives to natural aggregates [25]. Due to its relatively high melting point, bottom ash can contribute to the thermal stability of bituminous mixtures [13, 25]. Bottom ash has been used as structural filling materials for the construction of highway embankments, trenches, retaining walls and the backfilling of abutments. Bottom ash has been utilized as a substitute for finer fraction aggregates in base courses and hot mix asphalt wearing surfaces as well as emulsified asphalt cold mix for the same purposes. Due to the low durability and clinker-like popcorn nature of bottom ash particles, it is more commonly used in base courses than in wearing surfaces of bituminous pavements. Also, there are no reported applications of bottom ash fractions in asphalt surface treatments or seal coats [26].

Table 3 Physical properties of bottom ash

Sr. No.	Moisture Content (%) [27]	Specific Gravity [27-29]	Water Absorption (%) [29-32]	Fineness Modulus [29, 30, 33]	Surface Area (cm ² /g) [34, 35]
1	-	1.39	6.8	1.5	3835.75
2	0.43	2.41	31.58	3.44	10,500
3	-	2.22	20.15	2.71	-

Table 4 Chemical composition of bottom ash

Sr. No.	Chemical composition (%)										References
	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	TiO ₂	P ₂ O ₅	SO ₃	
1	62.33	25.52	4.16	1.00	0.94	0.08	3.2	0.84	0.12	-	[36]
2	59.82	27.76	3.77	1.86	0.70	1.61	0.33	-	-	1.39	[37]
3	58.7	20.1	6.2	9.5	1.6	0.1	1.0	-	1.0	0.4	[38]
4	68.9	18.67	6.5	1.61	0.53	0.24	1.52	1.33	-	-	[39]
5	54.8	28.5	8.49	4.2	0.35	0.08	0.45	2.71	0.28	-	[40]
6	52.5	17.65	8.30	4.72	0.58	-	-	2.17	-	0.84	[41]

2.3 Cenospheres

Cenospheres is a waste product in the composition of fly-ash burning coal in thermal power plants, as a result of complex thermochemical processes [42]. These are lightweight, hollow, spherical particles composed primarily of silica and alumina found within fly ash. They are characterized by their uniform shape and low density, making them ideal for reducing the overall weight of bituminous mixtures without compromising strength. Cenospheres constitute an average mass fraction of 0.01 to 4.80% within fly ash. They possess distinctive features, including a low bulk density ranging from 0.4 to 0.72 g·cm⁻³, extremely low thermal conductivity approximately 0.065 W·m⁻¹·K⁻¹ and remarkable stability when exposed to alkaline environments and higher temperatures. The size of cenosphere particles vary between approximately 5 and 500 µm [42, 43]. In terms of their chemical composition, these materials are characterized as multi-component systems, with a SiO₂-Al₂O₃-Fe₂O₃ content nearing 90% [44-46]. Cenospheres have the lowest carbon content among the coal ash types, which enhances their utility in applications where low carbon content is desirable [7]. A promising material for obtaining syntactic foam is cenospheres, hollow aluminosilicate microballoons [42]. The global market for cenospheres is valued at approximately USD 600 million per year, which corresponds to an output of 700-800 tonnes [47, 48]. The primary producers of cenospheres on a global scale include China, India, Russia, Kazakhstan and Ukraine. As a byproduct of thermal power plants operations, cenospheres is accessible at a relatively economical price [49]. Their hollow structure provides good thermal insulating properties, which can be suitable in applications where temperature regulation is critical. Cenospheres are used in some special type of bituminous mixtures where weight reduction is significant such as in lightweight asphalt pavements and overlays.

2.4 Boiler slag

Boiler slag is a byproduct of wet-bottom boilers which is glassy & granular in nature formed when molten ash is quenched in water. It is known for its angular shape and hardness. When pulverized coal undergoes combustion within a slag-tap furnace, approximately 50 percent of the resultant ash is retained within the furnace as boiler slag. Conversely, in a cyclone furnace that utilizes crushed coal for combustion, a significant proportion of 70% – 80% of the ash is retained as boiler slag with merely 20% – 30% exiting the furnace in the form of fly ash particles [50]. The table 5 shows some important physical and mechanical properties of boiler slag. From table 5 it is seen that the maximum dry density (MDD) of boiler slag is generally

from 12% to 27% lower compared to that of naturally available granular materials. Also, table 6 shows the chemical composition of boiler slag obtained from West Virginia and North Dakota of United States. From table 6 it is seen that the boiler slag derived from lignite or sub-bituminous coals has a higher percentage of calcium than the bottom ash or boiler slag from anthracite or bituminous coals [26]. The angular shaped particles of boiler slag provide excellent interlocking and skid resistance in asphaltic surfaces [51]. The high hardness of boiler slag contributes to the durability and wearing resistance of bituminous mixtures. The dark color of boiler slag can enhance the aesthetic look of asphalt surfaces specially in decorative or high-visibility applications [52]. Boiler slag has also been used as an aggregate in bituminous paving application, as a structural filling [53] as well as in road base & sub-base preparations [54]. Boiler slag has been used in base courses, wearing surfaces and seal coat applications or asphalt surface treatment [26]. Boiler slag sometimes have been used as unbound fine aggregate or for stabilized base applications and as a granular base material for pavement construction [26]. The salt content and in certain instances, the low pH of bottom ash and boiler slag may result in corrosive properties. When using bottom ash or boiler slag in an embankment, backfill, sub-base or even possibly in a base course application, the potential for corrosion of metal structures that may come in contact with the material is of concern and should be evaluated prior to use [26].

Table 5 Physical and mechanical properties of boiler slag [26]

Sr. No.	Property	Results
1	Dry Unit Weight (kg/m ³) [55]	960-1440
2	Specific Gravity [55]	2.3-2.9
3	Plasticity [55]	-
4	Water absorption (%) [56]	0.3-1.1
5	Particle size distribution - No. 4 to No. 40 sieve (mm) [56]	5.0 to 0.5
6	Maximum Dry Density (kg/m ³) [57]	1330-1650
7	Optimum Moisture Content (%) [57]	8-20

Table 6 Chemical composition of boiler slag [26, 56]

Sr. No.	Chemical composition (%)	Bituminous Coal	Lignite Coal
		West Virginia	North Dakota
1	SiO ₂	53.6-48.9	40.5
2	Al ₂ O ₃	22.7-21.9	13.8
3	Fe ₂ O ₃	14.3-10.3	14.2
4	CaO	1.4	22.4
5	MgO	5.2	5.6
6	Na ₂ O	1.2-0.7	1.7
7	K ₂ O	0.1	1.1
8	SO ₂	< 0.1	< 0.1

3. Performance of coal ash in bituminous mixtures

The application of coal ash in bituminous mixtures primarily impacts the performance characteristics of bituminous pavements. This section deals with the main performance parameters that are influenced by coal ash such as stability, durability, moisture resistance environmental impact and also cost-benefit analysis.

3.1 Stability and rutting resistance

The stability & rutting resistance of bituminous mixtures is primarily affected by the addition of coal ash, mainly coal bottom ash (CBA) as a filler & fine aggregate instead of conventional materials. The research has demonstrated that utilizing CBA in bituminous mixtures can improve their performance characteristics such as stability and resistance to rutting. The study by Muhammad Kamran et al. evaluated different percentages of CBA as a mineral filler in hot mix asphalt. The results indicated that adding up to 3% CBA by volume of mix enhanced the rutting resistance, stiffness of the asphalt mixtures as well as their fatigue life. This suggests that CBA can effectively replace conventional fillers like stone dust giving a sustainable disposal method for coal ash while increasing the mechanical properties of the asphalt mixtures [58]. Similarly, another study investigated the effects of varying proportions of CBA (0%, 2%, 4% and 6%) on the engineering characteristics of bituminous mixes. The findings revealed that the CBA addition of 2% - 4% yielded the best results in terms of Marshall test parameters. The study concluded that the addition of CBA enhances the performance of asphalt mixes primarily in terms of stability and resistance to deformation under load [59]. The use of coal ash mainly fly ash, as a filler in bituminous mixtures has also been explored in other studies. For instance, Saswat Biswapriya Dash et al. investigated the performance of bituminous concrete composites utilizing fly ash as a substitute for conventional filler materials. The results showed that the modified bituminous concrete mix made with coal ash showed better performance than conventional mixes indicating that coal ash can enhance the mechanical properties of bituminous mixtures [13]. Moreover, the review by Ankita Dhiman highlighted that the various fillers including coal ash can improve the rutting resistance, stiffness & resistance to moisture of bituminous mixes. Further, the addition of fillers like coal ash makes the mix stiffer and more durable which is critical for improving the stability and resistance to rutting of pavements [60]. The study by Apinun Buritatum et al. investigated the use of bottom ash (BA) from coal-based power plants as a fine aggregate in asphalt concrete. The findings demonstrated that utilizing BA improved the Marshall stability, flow and indirect tensile strength of the bituminous mixes. The optimum BA replacement percentage was found to be 5% which resulted in improved rutting resistance and skid resistance as well as a reduction in permanent deformation & rut depth. These improvements are allotted to the efficient interaction of BA with the bituminous binder, which subsequently enhances the mechanical performance of the bituminous concrete mixes [61]. In another study CBA was used as a mechanical stabilizer in subgrade soil which indirectly supports the stability of the overlying bituminous layers. The addition of CBA improved the California bearing ratio values and reduced the swelling potential of the soil, indicating enhanced load-bearing capacity and stability. This suggests that coal bottom ash can contribute to the overall stability of pavement structures by improving the properties of the subgrade [62]. In a study conducted by Colonna P. et al. regarding the utilization of bottom ash in the composition of pavement binder course, optimal outcomes have been realized when a 15% proportion of BA was

incorporated into the mixture, substituting an equivalent volume of sand. An increase in asphalt content correlates positively with enhanced wearing resistance of the composite mixes. The experimental findings suggest that there is no degradation in the mechanical properties of the asphalt mixture when compared to the traditional reference mixture [63]. Ksaibati [64] the viability of employing CBA as a total substitute for aggregates. Both coarse CBA and fine CBA were utilized in hot mix asphalt and subjected to evaluations in both field and laboratory environments. A total of three samples examined were prepared by using CBA sourced from the three distinct origins. The findings indicated that the optimal bitumen content was increased in the mixes incorporating CBA, with no discernible difference in the mechanical performance between CBA mixes and the control mix following their service period. The laboratory investigations revealed that all evaluated hot mix asphalt mixtures exhibited diverse characteristics regarding cracking at low & high temperature suggesting that the differing physical characteristics of the CBA derived from different thermal power stations may influence the integrity of the bituminous mixes [64]. Fly ash, another form of coal ash has been used as a filler substitute in asphalt concrete base courses. The performance analysis revealed that mixtures with higher percentages of fly ash exhibited better durability, with a 15% fly ash mixture showing superior performance compared to lower percentages [65]. The use of coal fly ash (CFA) as a filler enhances the mixture's resistance to rutting and fatigue, which are indirectly related to tensile strength [66, 67]. The addition of CFA in varying percentages (0%, 2%, 4%, and 6%) has been tested, with results indicating improved stability and moisture resistance, which contribute to better tensile performance [67]. Utilizing CBA as a filler-fraction substitute in asphalt mixes led to a higher rutting potential and a reduced dynamic modulus compared to control mixes [68]. Overall, the incorporation of coal ash, particularly bottom ash into bituminous mixtures can enhance stability and rutting resistance, provided that the optimal replacement ratios are identified and adhered to.

3.2 Durability and moisture resistance

The durability and moisture resistance of bituminous mixtures can be mainly influenced by the addition of coal ash, as evidenced by various studies. As per the study conducted by Kandhal and Rickards, moisture susceptibility in bituminous mixtures is a main cause of stripping which occurs when water infiltrates into the pavement, weakening the bond between the bitumen binder and aggregates. This leads to the loss of pavement materials and the formation of potholes & cracks on top surfaces ultimately necessitating costly repairs [69]. The pozzolanic properties of fly ash have been shown to improve the moisture resistance of bituminous mixtures by forming secondary cementitious compounds that strengthen the adhesion between the bitumen binder and the aggregates [70]. Research indicates that coal ash can act as an adhesion improver in bituminous mixes strengthening the resistance to moisture damage. A study evaluating coal ash as a bonding enhancement agent found that utilizing 4% coal ash in bituminous mixtures yielded moisture damage resistance comparable to mixtures containing natural fillers. The amalgamation of coal ash with lime further increases resistance to moisture damage, although the specific class of ash (Class C or Class F) did not significantly affect the results [71]. The investigations into the resistance to moisture susceptibility & fatigue cracking of asphalt mixtures using bottom ash and fly ash were conducted by Byung-Soo Yoo et al. [72]. The findings indicate that coal ash can be effectively used as fine aggregates in bituminous mixtures. The addition of bottom ash does not alter the moisture

susceptibility. Concerning the resistance to fatigue cracking, the findings from the repeated indirect tensile test conducted under dynamic loading conditions indicated that asphalt mixtures incorporating 5% coal ash shows improved resistance to fatigue cracking [72]. In stone mastic asphalt mixtures, the use of class C fly ash as a filler additive has been shown to significantly improve resistance to moisture damage [73]. This improvement is likely due to the formation of hydration products that enhance the structural integrity of the asphalt. Similarly, in cold mix asphalt, fly ash when used in combination with rice husk ash as an activator, has been found to improve moisture resistance and rutting performance [74]. Another study by Huang et al. found that fly ash-modified bituminous mixtures exhibited better resistance to freeze-thaw cycles, which are a common cause of moisture-related distress in pavements. The pozzolanic reaction between fly ash and calcium hydroxide in the presence of moisture results in the formation of calcium silicate hydrates (C-S-H), which improve the cohesion within the mixture thereby enhancing its durability [75]. A study on porous asphalt concrete (PAC) demonstrated that replacing fine aggregates with bottom ash improved several key properties such as Marshall stability, indirect tensile strength and rut resistance. The optimum replacement ratio was found to be 20% which also resulted in a significant reduction in construction costs compared to conventional polymer-modified asphalt [76]. Ameli et al. [77] investigated the efficacy of bituminous mixtures containing varying proportions of coal waste ash specifically at 0, 25, 50, 75 and 100%. The CBA particles were utilized as a substitute for traditional fillers. This study assessed the resistance to rutting and fatigue behavior of the mastics as well as stability value, dynamic creep, resilient modulus and moisture susceptibility of bituminous mixes. The findings revealed that incorporating coal waste ash enhanced the fatigue character of the mixes with further improvement observed when the mixes were modified using SBS. However, the substitution of coal waste ash led to a reduction in resilient modulus, rutting characteristics, Marshall stability and tensile strength of bituminous mixes, while concurrently enhancing resistance to moisture [77]. Xu et al. [78] conducted an examination of the influence of coal waste ash which had undergone a treatment process involving reheating on bituminous mastic as well as asphalt composites. The coal waste ash was employed as a substitute in varying proportions of 20, 40, 60 and 80%. In comparison to limestone powder, coal waste ash exhibited a less density, increased alkalinity, reduced particle sizes & a greater volume of internal air voids. The bitumen that included coal waste ash demonstrated a decreased penetration value, an increased softening point and enhanced thermal stability. Nevertheless, the integration of coal waste ash led to a reduction in both the rutting resistance and Marshall stability of the bituminous composite. Conversely, the resistance to moisture susceptibility of the bituminous composite showed marked improvement with the utilization of coal waste ash. Modarres and Ayar [79] investigated the influence of incorporating coal waste powder and coal waste ash as supplementary materials in a cold recycled mixes composed entirely of reclaimed asphalt pavement (RAP) constituents, utilizing technology of emulsified cold recycling with the additives' particle sizes being less than 0.0075 cm. Incorporation of coal waste powder and coal waste ash in varying proportions of 3, 5 and 7% significantly improved the engineering characteristics of the bituminous pavement. The increased pozzolanic percentage present in the coal waste powder contributed positively to the Marshall stability, tensile strength & resilient modulus. In comparison of coal waste powder, the coal waste ash exhibited superior efficacy in terms of moisture sensitivity and improved resistance to moisture-induced damage. Results show that the CBA, when used

as a fine aggregate in bituminous mixtures improves the mix's resistance to moisture-induced damage due to its angularity and rough surface texture which advances better bonding with the bitumen. Boiler slag with its hard and angular particles, has been shown to improve the skid resistance of bituminous surfaces while also contributing to moisture resistance.

3.3 Environmental impact

The long-term effects of using coal ash in bituminous mixes on environmental sustainability are complex involving both promising benefits and challenges. One of the primary advantages of utilizing coal ash into bituminous mixes is the enhancement of sustainability through waste valorization. By incorporating coal ash, the need for virgin as well as conventional materials is reduced which line up with circular economy principles and helps in mitigating the environmental impact associated with derivation & processing of raw materials [80, 81]. This scientific approach not only helps in waste management but also contributes to the reduction of landfill use thus preserving the natural resources [82]. From the technical perspective coal ash can enhance the mechanical properties of bituminous mixes. Studies have shown that coal ash can improve the compressive strength and toughness of construction materials which is needed for the longevity of pavements [83]. This improvement in the mechanical properties can lead to longer-lasting pavements reducing the frequency of repairs and associated environmental impacts over the longer time savings in the maintenance cost. However, the environmental sustainability of using coal ash in bituminous mixes is not without the challenges. One significant problem is the potential leaching of heavy metals from coal ash which could pose environmental and human health risks. While some studies have indicated that the concentration of heavy metals in coal ash mixtures is below regulatory limits, so to ensure the safety continuous monitoring and stringent testing are necessary [83]. Moreover, the life cycle assessment (LCA) of using coal ash in bituminous mixes shows mixed results. While the application of coal ash can reduce global warming problem and fossil resource scarcity, it may also increase the overall consumption of natural or fossil resources due to higher bitumen content requirements in some cases [80]. Sustainable pavements using recycled materials, including coal ash, can reduce energy consumption and emissions by about 45% compared to traditional asphalt pavements [84]. This highlights the need for a balanced approach that signifies both the environmental advantages and prominent drawbacks. In terms of long-term environmental sustainability, the use of coal ash in the bituminous mixes presents an optimistic opportunity to improve the sustainability of road construction. However, it requires careful consideration of the environmental impacts throughout the material's life cycle. The integration of coal ash should be associated by comprehensive environmental assessments and according to regulatory standards to minimize any adverse effects during the utilization of it. In conclusion, while the use of coal ash in bituminous mixes offers significant potential for improving environmental sustainability by reducing waste and saving natural resources, it also necessitates careful management of potential environmental risks. Ongoing research and development along with vigorous environmental monitoring are essential to fully realize the benefits while minimizing any negative impacts [80, 81, 83].

3.4 Cost-benefit analysis of coal ash in bituminous mixtures

The cost-benefit analysis of incorporating coal ash in bituminous mixtures reveals both economic and environmental advantages. Coal ash, a by-product of coal combustion, can be

effectively utilized in construction materials, particularly in bituminous mixtures, to enhance their properties while addressing waste disposal issues. This analysis considers the economic savings, environmental benefits and technical feasibility of using coal ash in bituminous mixtures.

3.5 Economic benefits

Utilizing coal ash in bituminous mixtures can lead to significant cost savings. For instance, the application of CBA as a microfiller in cement concrete can reduce production costs by up to 3.6% due to decreased cement consumption [85]. Similarly, the use of pond ash in pavement construction can achieve direct cost savings of around 10% [86]. By replacing conventional materials with coal ash, the acquisition and disposal costs are reduced. This is particularly beneficial in highway construction, where the use of ash as a replacement for mineral filler in hot-mix asphalt concrete saves material costs up to 12% [87]. The construction of asphalt necessitates a substantial quantity of naturally available aggregates, specifically 100% aggregates for the sub-base & base layers, 95% for bituminous paving layers, and 87% for cement concrete pavements. The amount of natural aggregates required to build one kilo-meter of a surface layer employing an asphalt mix may surpass 15,000 metric tons [88]. In contemporary times, the substitution of natural aggregates with coal bottom ash has led to a decrease in construction expenses and diminished the necessity to extract aggregates from ecological resources.

3.6 Environmental benefits

The incorporation of coal ash in bituminous mixtures helps in managing the disposal of this waste product, thereby reducing environmental pollution. The utilization of coal ash in construction materials prevents the harmful effects of ash disposal on land, air and water [89, 90]. By substituting coal ash for natural aggregates, the demand for mined resources is decreased, leading to conservation of natural materials and a reduction in the environmental impact of resource extraction [91, 92]. By substituting coal ash for traditional materials, there is a reduction in CO₂ emissions associated with the production of these materials. This contributes to a more sustainable construction practice [90]. The use of waste biomass ash in bituminous concrete mixes has been shown to be 62% more environmentally friendly compared to conventional mixes, highlighting the potential for significant environmental benefits [93]. CBA represents an eco-friendly resource capable of mitigating detrimental ecological effects while fostering sustainability in the manufacturing of concrete [94].

3.7 Technical feasibility

Coal ash enhances the engineering properties of bituminous mixtures. The cementitious properties of coal ash contribute to improved strength and durability of the mixtures [95]. Additionally, coal ash has shown good technical feasibility in asphalt mixes, maintaining mechanical performance comparable to traditional materials [96]. Studies have demonstrated that coal ash can be effectively used as a filler in bituminous paving mixes without compromising the desired properties. For example, fly ash used as a mineral filler in bituminous paving mixes meets the required specifications and offers a viable alternative to traditional fillers [97].

4. Challenges and Future Research Scope

While the applications of coal ash in bituminous mixtures offers several advantages, there are also some challenges that must be addressed to ensure its successful utilization. One of the primary challenges in using coal ash is the heterogeneity in the chemical and physical properties. This variability can affect the consistency and performance of the prepared bituminous mixtures. The best solution is numerous blending of coal ash from different sources or with other materials, which can help achieve more consistent and stable properties. Secondly, the use of coal ash in construction is subject to regulatory surveillance, mostly concerning environmental impact and human health. The perfect solution is to implement accurate rigorous environmental monitoring programs to track the long-term impact of coal ash in bituminous pavement mixtures.

Current research is important to explore new applications of coal ash and enhance its performance in bituminous mixes. The following are the important points one needs to consider regarding future research.

1. Investigating the microstructural properties of coal ash and their influence on asphalt performance.
2. To study the coal ash utilization in dense bituminous macadam along with some natural or conventional fibers.
3. Exploring the use of coal ash in innovative asphalt technologies, such as warm-mix asphalt and porous pavements with some additives.
4. Conducting comprehensive lifecycle assessments to quantify the environmental and economic benefits of using coal ash in bituminous mixtures.
5. To achieve a higher degree of environmental sustainability, it is necessary to investigate the application of coal ash at a rate of 15 to 20% in bituminous road pavements.

5. Conclusion

The utilization of coal ash in bituminous mixtures represents a promising strategy for the advancement of sustainable road construction methodologies. By capitalizing on the distinctive characteristics of fly ash, bottom ash, cenospheres and boiler slag, civil engineers can significantly improve the performance attributes of asphalt pavements while concurrently mitigating environmental impacts. From an extensive review of the literature, it has been determined that the integration of coal bottom ash within a range of 2% to 4% yields optimal outcomes in terms of density, stability, stiffness and flow characteristics for bituminous pavement applications. In addition, the ideal ratio for bottom ash and fly ash substitution was determined to be 5%, which led to improved resistance to rutting and skidding, alongside a decrease in permanent deformation and rut depth. The pozzolanic attributes of fly ash have demonstrated the capability to enhance the moisture resistance of bituminous mixtures by generating secondary cementitious compounds that fortify the adhesion between the bitumen and the aggregates. Cost-benefit analysis of coal ash modified blends shows that up to 12% saving in the material cost while producing hot bituminous mixes and 50% reduction in CO₂ emission while producing cement concrete materials which ultimately leads to sustainable

pavement construction practices. It is observed that limited researchers studied the use of fly ash and bottom ash combinedly in the bituminous pavement beyond 15%. Also, the combined use of fly ash as filler and bottom ash as fine aggregates in dense bituminous Macadam is rarely studied along with suitable fibers which needs in depth exploration. Nevertheless, challenges such as the heterogeneity of coal ash composition and regulatory issues necessitate resolution through ongoing research, standardization efforts and rigorous environmental monitoring. As the construction sector increasingly emphasizes sustainability, coal ash possesses the potential to assume a crucial role in the formulation of more ecologically responsible and resilient infrastructure systems.

References

1. Bhatt A, Priyadarshini S, Acharath Mohanakrishnan A, et al (2019) Physical, chemical, and geotechnical properties of coal fly ash: A global review. *Case Studies in Construction Materials* 11:e00263. <https://doi.org/10.1016/j.cscm.2019.e00263>
2. Nursanto E, Ilcham A (2020) Characteristics of Coal and Coal Ash. In: Gedung Rektorat (ed) *Proceeding of LPPM UPN "Veteran" Yogyakarta Conference Series 2020 – Engineering and Science (ESS)*. Yogyakarta, RSF Press & Research Synergy Foundation, Bandung, Indonesia
3. Mr. Sonawane SK, Dr. Vyawahare MR, Mrs. Chitkeshwar CA (2018) Influence of Filler Combination on the Bituminous Mixes. *International Journal of Advanced Research Trends in Engineering and Technology (IJARTET)* 5:4–11
4. Chandra S, Choudhary R (2013) Performance Characteristics of Bituminous Concrete with Industrial Wastes as Filler. *Journal of Materials in Civil Engineering* 25:1666–1673. [https://doi.org/10.1061/\(asce\)mt.1943-5533.0000730](https://doi.org/10.1061/(asce)mt.1943-5533.0000730)
5. Report on Fly Ash Generation at Coal / Lignite Based Thermal Power Stations and its Utilization in the Country for the 1st Half of the Year 2022 – 2023 (2023). New Delhi, India
6. Ram AK, Mohanty S (2022) State of the art review on physiochemical and engineering characteristics of fly ash and its applications. *Int J Coal Sci Technol* 9:9. <https://doi.org/10.1007/s40789-022-00472-6>
7. Beddu S, Basri NAN, Mohd Kamal NL, et al (2024) Characterization of Coal Combustion Products from Malaysian Power Plant for Building Materials Applications. *MATEC Web of Conferences* 400:01007. <https://doi.org/10.1051/matecconf/202440001007>
8. Singh AK, Masto RE, Hazra B, et al (2020) Genesis and Characteristics of Coal and Biomass Ash. In: *Ash from Coal and Biomass Combustion*. Springer International Publishing, Cham, pp 15–36
9. ASTM International (2018) *Concrete and aggregates*. West Conshohocken, PA, USA.
10. ASTM International (2022) *ASTM C618-22 Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete*
11. Bureau of Indian Standards (2003) *IS 3812-1: Specification for Pulverized Fuel Ash, Part 1: For Use as Pozzolana in Cement, Cement Mortar and Concrete*
12. Ismail KN, Hussin K, Sobri M, et al (2007) Physical, Chemical & Mineralogical Properties of Fly Ash. *Journal of Nuclear and Related Technology* 4:47–51
13. Dash SB, Panda M (2016) A Study on Use of Natural Fiber for Improvement in Engineering Properties of Dense Graded Bituminous Mixes with Coal Ash. *Transportation in Developing Economies* 2:4. <https://doi.org/10.1007/s40890-015-0008-z>
14. Pandian NS (2004) Fly ash characterization with reference to geotechnical applications. *J Indian Inst Sci* 84:189–216
15. Blissett RS, Rowson NA (2012) A review of the multi-component utilisation of coal fly ash. *Fuel*

- 97:1–23. <https://doi.org/10.1016/J.FUEL.2012.03.024>
16. Ghosh A, Subbarao C (1998) Hydraulic Conductivity and Leachate Characteristics of Stabilized Fly Ash. *Journal of Environmental Engineering* 124:812–820. [https://doi.org/10.1061/\(ASCE\)0733-9372\(1998\)124:9\(812\)](https://doi.org/10.1061/(ASCE)0733-9372(1998)124:9(812))
17. British Petroleum (2018) BP Energy Outlook 2018 edition
18. Feuerborn HJ (2009) Calcereous Ash in Europe- a reflection on technical and legal issues. In: 2nd Hellenic Conference on Utilization on Industrial By-Products in Construction. Aiani Kozani, Greece, pp 1–3
19. Wesche K (1991) Fly Ash in Concrete. CRC Press
20. Belviso C, Cavalcante F, Fiore S (2010) Synthesis of zeolite from Italian coal fly ash: Differences in crystallization temperature using seawater instead of distilled water. *Waste Management* 30:839–847. <https://doi.org/10.1016/j.wasman.2009.11.015>
21. Binal A, Bas B, Karamut OR (2016) Improvement of the Strength of Ankara Clay with Self-cementing High Alkaline Fly Ash. *Procedia Eng* 161:374–379. <https://doi.org/10.1016/j.proeng.2016.08.577>
22. United States Environmental Protection Agency (2015) Frequent Questions about the 2015 Coal Ash Disposal Rule. <https://www.epa.gov/coalash/frequent-questions-about-2015-coal-ash-disposal-rule>. Accessed 10 Oct 2024
23. Churchill EV, Amirkhanian SN (1999) Coal Ash Utilization in Asphalt Concrete Mixtures. *Journal of Materials in Civil Engineering* 11:295–301. [https://doi.org/10.1061/\(ASCE\)0899-1561\(1999\)11:4\(295\)](https://doi.org/10.1061/(ASCE)0899-1561(1999)11:4(295))
24. Milad A, Ali ASB, Babalghaith AM, et al (2021) Utilisation of Waste-Based Geopolymer in Asphalt Pavement Modification and Construction—A Review. *Sustainability* 13:3330. <https://doi.org/10.3390/su13063330>
25. Abdullah MH, Rashid ASA, Anuar UHM, et al (2019) Bottom ash utilization: A review on engineering applications and environmental aspects. *IOP Conf Ser Mater Sci Eng* 527:012006. <https://doi.org/10.1088/1757-899X/527/1/012006>
26. Federal Highway Administration (2016) User Guidelines for Waste and Byproduct Materials in Pavement Construction. Washington, DC
27. Onprom P, Chaimoon K, Cheerarot R (2015) Influence of Bottom Ash Replacements as Fine Aggregate on the Property of Cellular Concrete with Various Foam Contents. *Advances in Materials Science and Engineering* 2015:1–11. <https://doi.org/10.1155/2015/381704>
28. Topcu IB, Bilir T (2010) Effect of Bottom Ash as Fine Aggregate on Shrinkage Cracking of Mortars. *ACI Mater J* 107:48–56. <https://doi.org/10.14359/51663465>
29. Baite E, Messan A, Hannawi K, et al (2016) Physical and transfer properties of mortar containing coal bottom ash aggregates from Tefereyre (Niger). *Constr Build Mater* 125:919–926. <https://doi.org/10.1016/j.conbuildmat.2016.08.117>
30. Singh N, M M, Arya S (2019) Utilization of coal bottom ash in recycled concrete aggregates based self compacting concrete blended with metakaolin. *Resour Conserv Recycl* 144:240–251. <https://doi.org/10.1016/j.resconrec.2019.01.044>
31. Singh M, Siddique R (2016) Effect of coal bottom ash as partial replacement of sand on workability and strength properties of concrete. *J Clean Prod* 112:620–630. <https://doi.org/10.1016/j.jclepro.2015.08.001>
32. Singh M, Siddique R (2014) Strength properties and micro-structural properties of concrete containing coal bottom ash as partial replacement of fine aggregate. *Constr Build Mater* 50:246–256. <https://doi.org/10.1016/j.conbuildmat.2013.09.026>
33. Rafieizonooz M, Mirza J, Salim MR, et al (2016) Investigation of coal bottom ash and fly ash in concrete as replacement for sand and cement. *Constr Build Mater* 116:15–24. <https://doi.org/10.1016/j.conbuildmat.2016.04.080>
34. Kiruthiga P, Dave N, Guduru R (2022) A Critical Review on the application of coal Bottom Ash

- inconcrete: An Indian Prospective. IOP Conf Ser Mater Sci Eng 1258:012064. <https://doi.org/10.1088/1757-899X/1258/1/012064>
35. Hashemi SSG, Mahmud H Bin, Ghuan TC, et al (2019) Safe disposal of coal bottom ash by solidification and stabilization techniques. Constr Build Mater 197:705–715. <https://doi.org/10.1016/j.conbuildmat.2018.11.123>
 36. Wie YM, Lee KG (2020) Composition design of the optimum bloating activation condition for artificial lightweight aggregate using coal ash. Journal of the Korean Ceramic Society 57:220–230. <https://doi.org/10.1007/s43207-020-00025-0>
 37. Ge X, Zhou M, Wang H, et al (2018) Preparation and characterization of ceramic foams from chromium slag and coal bottom ash. Ceram Int 44:11888–11891. <https://doi.org/10.1016/j.ceramint.2018.03.122>
 38. Oruji S, Brake NA, Nalluri L, Guduru RK (2017) Strength activity and microstructure of blended ultra-fine coal bottom ash-cement mortar. Constr Build Mater 153:317–326. <https://doi.org/10.1016/j.conbuildmat.2017.07.088>
 39. Ibrahim MHW, Hamzah AF, Jamaluddin N, et al (2015) Split Tensile Strength on Self-compacting Concrete Containing Coal Bottom Ash. Procedia Soc Behav Sci 195:2280–2289. <https://doi.org/10.1016/j.sbspro.2015.06.317>
 40. Syahrul Hisyam bin Mohd Sani M, bt Muftah F, Muda Z (2010) The Properties of Special Concrete Using Washed Bottom Ash (WBA) as Partial Sand Replacement. International Journal of Sustainable Construction Engineering & Technology 1:65–76
 41. Mangi SA, Wan Ibrahim MH, Jamaluddin N, et al (2019) Short-term effects of sulphate and chloride on the concrete containing coal bottom ash as supplementary cementitious material. Engineering Science and Technology, an International Journal 22:515–522. <https://doi.org/10.1016/j.jestech.2018.09.001>
 42. Ranjbar N, Kuenzel C (2017) Cenospheres: A review. Fuel 207:1–12. <https://doi.org/10.1016/j.fuel.2017.06.059>
 43. Shao Y, Jia D, Liu B (2009) Characterization of porous silicon nitride ceramics by pressureless sintering using fly ash cenosphere as a pore-forming agent. J Eur Ceram Soc 29:1529–1534. <https://doi.org/10.1016/j.jeurceramsoc.2008.09.012>
 44. Rohatgi PK, Matsunaga T, Gupta N (2009) Compressive and ultrasonic properties of polyester/fly ash composites. J Mater Sci 44:1485–1493. <https://doi.org/10.1007/s10853-008-3165-1>
 45. Anshits NN, Vereshchagina TA, Bayukov OA, et al (2005) The Nature of Nanoparticles of Crystalline Phases in Cenospheres and Morphology of Their Shells. Glass Physics and Chemistry 31:306–315. <https://doi.org/10.1007/s10720-005-0060-6>
 46. McBride SP, Shukla A, Bose A (2002) Processing and characterization of a lightweight concrete using cenospheres. J Mater Sci 37:4217–4225. <https://doi.org/10.1023/A:1020056407402>
 47. Adesina A (2020) Sustainable application of cenospheres in cementitious materials – Overview of performance. Developments in the Built Environment 4:100029. <https://doi.org/10.1016/j.dibe.2020.100029>
 48. Markets and Markets (2022) Cenosphere Market by Type (Gray Cenosphere, White Cenosphere) End-Use Industry (Refractory, Construction, Oil and Gas, Automotive, Paints and Coatings) and Region-Global Forecast.
 49. Shishkin A, Abramovskis V, Zalite I, et al (2023) Physical, Thermal, and Chemical Properties of Fly Ash Cenospheres Obtained from Different Sources. Materials 16:2035. <https://doi.org/10.3390/ma16052035>
 50. Babcock & Wilcox Company (2015) STEAM / its generation and use, 42nd ed. B&W, New York
 51. Roy M, Kumar A, Janardhana M (2014) Study on the effects of coal-ash-slag deposition on boiler tubes in a coal-fired thermal power plant. Power Research - A Journal of CPRI 10:611–616
 52. Craig H. Benson, Sabrina Bradshaw (2011) User Guideline for Coal Bottom Ash and Boiler Slag in Green Infrastructure Construction. Madison, USA

53. American Society for Testing and Materials (1997) ASTM E1861-97 - Standard Guide for Use of Coal Combustion By-Products in Structural Fills. West Conshohocken, Pennsylvania
54. Hecht NL, Duvall DS (1975) Characterization and utilization of municipal and utility sludges and ashes: Volume III - Utility coal ash. United States
55. Majizadeh, Kamran, Bokowski G, El-Mitiny R (1979) Material Characteristics of Power Plant Bottom Ashes and Their Performance in Bituminous Mixtures: A Laboratory Investigation. In: Proceedings of the Fifth International Ash Utilization Symposium. U.S. Department of Energy, Report No. METC/SP-79/10, Part 2, Morgantown, West Virginia
56. Moulton, Lyle K. (1973) Bottom Ash and Boiler Slag. In: Proceedings of the Third International Ash Utilization Symposium. U.S. Bureau of Mines, Information Circular No. 8640, Washington, DC
57. Lovell CW, T.-C. Ke, W.-H. Huang, J. E. Lovell (1991) Bottom Ash as Highway Material. Washington, D.C.
58. Kamran M, Khan MT, Khan D, et al (2023) Experimental evaluation of hot mix asphalt using coal bottom ash as partial filler replacement. Roads and Bridges - Drogi i Mosty 22:167–179. <https://doi.org/10.7409/rabdim.023.008>
59. Ing NLS, Ming NC, Hasan M, et al (2022) The Influence of Coal Bottom Ash as Filler in Asphalt Mixture. Key Eng Mater 912:185–198. <https://doi.org/10.4028/p-beny4x>
60. Ankita Dhiman, Ajay Kumar Duggal (2017) Role of Filler in the Enhancement of Properties of Bituminous Mixes: A Review. International Journal for Research in Applied Science & Engineering Technology (IJRASET) 5:1150–1154
61. Buritatum A, Suddepong A, Horpibulsuk S, et al (2022) Improved Performance of Asphalt Concretes using Bottom Ash as an Alternative Aggregate. Sustainability 14:7033. <https://doi.org/10.3390/su14127033>
62. Cadarsa AS, Seeborun AK, Chan Chim Yuk A (2014) Use of Coal Bottom Ash as Mechanical Stabiliser in Subgrade Soil. Journal of Engineering 2014:1–6. <https://doi.org/10.1155/2014/184607>
63. Colonna P, Berloco N, Ranieri V, Shuler ST (2012) Application of Bottom Ash for Pavement Binder Course. Procedia Soc Behav Sci 53:961–971. <https://doi.org/10.1016/J.SBSPRO.2012.09.945>
64. Ksaibati K (1999) Utilization Of Bottom Ash in Asphalt Mixes. Laramie, WY, USA
65. Archenita D, Alkhairi W, Rizki A, et al (2023) Durability Performance Analysis of Mixture Asphalt Concrete - Base Course (AC-Base) Using Coal Fly Ash as A Filler Substitute. International Journal of Advanced Science Computing and Engineering 5:31–43. <https://doi.org/10.62527/ijasce.5.1.120>
66. M. Radwan AA, Mohd Satar MKI, Abdul Hassan N, Mohd Warid MN (2024) Mechanical Properties of Hot Mix Asphalt Incorporating Coal Fly Ash Filler. pp 67–76
67. Radwan AAM, Satar MKIM, Hassan NA, Rogo KU (2022) The Influence of Coal Fly Ash on the Mechanical Properties of Hot Mix Asphalt Mixture. IOP Conf Ser Earth Environ Sci 971:012012. <https://doi.org/10.1088/1755-1315/971/1/012012>
68. Goh SW, You Z (2008) A preliminary study of the mechanical properties of asphalt mixture containing bottom ash. Canadian Journal of Civil Engineering 35:1114–1119. <https://doi.org/10.1139/L08-071>
69. Kandhal PS, Rickards IJ (2001) Premature Failure of Asphalt Overlays from Stripping: Case Histories (With Discussion). Journal of the Association of Asphalt Paving Technologists 70:301–351
70. Nataša J, Miodrag P, Ivana M (2012) Influence of Fly Ash on the Moisture Damage Resistance of Asphalt Mixtures. Constr Build Mater 30:11–18
71. Xavier M de F, Ferreira WLG, Branco VTFC (2020) Evaluation of coal ash use as an adhesion improver in asphalt mixtures. SciELO journals 25:. <https://doi.org/10.1590/s1517-707620200001.0891>

72. Yoo BS, Park DW, Vo HV (2016) Evaluation of Asphalt Mixture Containing Coal Ash. *Transportation Research Procedia* 14:797–803. <https://doi.org/10.1016/J.TRPRO.2016.05.027>
73. Çetin A (2022) The effect of filler additives on moisture damage in stone mastic asphalt (SMA) mixtures. *Journal of the Croatian Association of Civil Engineers* 73:1209–1221. <https://doi.org/10.14256/JCE.3321.2021>
74. Raj A, Sivakumar M, Anjaneyulu MVL (2023) Use of rice husk ash-activated fillers on rutting and moisture resistance of cold mix asphalt. *International Journal of Pavement Engineering* 24:.. <https://doi.org/10.1080/10298436.2022.2144307>
75. Huang B, Shu X, Dong Q, Shen J (2010) Laboratory Evaluation of Moisture Susceptibility of Hot-Mix Asphalt Containing Cementitious Fillers. *Journal of Materials in Civil Engineering* 22:667–673. [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0000064](https://doi.org/10.1061/(ASCE)MT.1943-5533.0000064)
76. Suddepong A, Buritatum A, Dasdawan S, et al (2023) Mechanical Performance of Porous Asphalt Concrete Incorporating Bottom Ash as Fine Aggregate. *Journal of Materials in Civil Engineering* 35:.. <https://doi.org/10.1061/JMCEE7.MTENG-15233>
77. Ameli A, Babagoli R, Norouzi N, et al (2020) Laboratory evaluation of the effect of coal waste ash (CWA) and rice husk ash (RHA) on performance of asphalt mastics and Stone matrix asphalt (SMA) mixture. *Constr Build Mater* 236:117557. <https://doi.org/10.1016/j.conbuildmat.2019.117557>
78. Xu P, Chen Z, Cai J, et al (2019) The effect of retreated coal wastes as filler on the performance of asphalt mastics and mixtures. *Constr Build Mater* 203:9–17. <https://doi.org/10.1016/j.conbuildmat.2019.01.088>
79. Modarres A, Ayar P (2014) Coal waste application in recycled asphalt mixtures with bitumen emulsion. *J Clean Prod* 83:263–272. <https://doi.org/10.1016/j.jclepro.2014.07.082>
80. Oreto C, Russo F, Dell’Acqua G, Veropalumbo R (2024) A comparative environmental life cycle assessment of road asphalt pavement solutions made up of artificial aggregates. *Science of the Total Environment* 927:171716. <https://doi.org/10.1016/J.SCITOTENV.2024.171716>
81. Nandal M, Sood H, Gupta PK (2023) A review study on sustainable utilisation of waste in bituminous layers of flexible pavement. *Case Studies in Construction Materials* 19:e02525. <https://doi.org/10.1016/J.CSCM.2023.E02525>
82. López-Montero T, Miró R, Martínez A (2023) Effect of the use of Marpol waste as a partial replacement of the binder for the manufacture of more sustainable bituminous mixtures. *International Journal of Pavement Engineering* 24:.. <https://doi.org/10.1080/10298436.2022.2046275>
83. Modarres A, Hesami S, Soltaninejad M, Madani H (2018) Application of coal waste in sustainable roller compacted concrete pavement-environmental and technical assessment. *International Journal of Pavement Engineering* 19:748–761. <https://doi.org/10.1080/10298436.2016.1205747>
84. Zhao W, Yang Q (2024) Life-cycle assessment of sustainable pavement based on the coordinated application of recycled asphalt pavement and solid waste: Environment and economy. *J Clean Prod* 434:140203. <https://doi.org/10.1016/j.jclepro.2023.140203>
85. Bumanis G, Bajare D, Korjamins A (2013) The Economic And Environmental Benefits from Incorporation of Coal Bottom Ash in Concrete. In: 4th International Conference Civil Engineering`13 Proceedings Part I CONSTRUCTION AND MATERIALS. pp 142–152
86. Sarkar R, Dawson AR (2017) Economic assessment of use of pond ash in pavements. *International Journal of Pavement Engineering* 18:578–594. <https://doi.org/10.1080/10298436.2015.1095915>
87. Serrano-Guzmán MF, Pérez-Ruiz DD, Vanegas NCS (2015) Use of Ash in Hot Dense Mixtures. *Transportation Research Record: Journal of the Transportation Research Board* 2473:66–71. <https://doi.org/10.3141/2473-08>
88. Ahmaruzzaman M (2010) A review on the utilization of fly ash. *Prog Energy Combust Sci* 36:327–363. <https://doi.org/10.1016/j.pecs.2009.11.003>
89. Santhosh Y, Mohammed K (2019) A Study On Use Of Natural Fiber By Dense Grade Bituminous

- Mixes With Coal Ash 06:531-541. International Journal of Research
90. Singh M (2018) Coal bottom ash. In: Waste and Supplementary Cementitious Materials in Concrete. Elsevier, pp 3–50
91. Lindon K. A. Sear (2008) Using Coal Fly Ash in Road Construction. In: LJMU 2008 Annual International Conference. Liverpool, UK
92. Butalia TS, Wolfe WE (2001) Utilization of coal combustion products in ohio for construction and repair of highways
93. Choudhary J, Kumar B, Singh S (2021) Assessment of engineering and environmental suitability of waste bituminous concrete containing waste biomass ash. International Journal of Pavement Research and Technology 14:751–763. <https://doi.org/10.1007/s42947-020-0242-6>
94. Ankur N, Singh N (2021) Performance of cement mortars and concretes containing coal bottom ash: A comprehensive review. Renewable and Sustainable Energy Reviews 149:111361. <https://doi.org/10.1016/j.rser.2021.111361>
95. Al NH, Al-Busaltan S (2012) Improvements in and relating to bituminous paving
96. BARRA B, MOMM L, GUERRERO Y, et al (2021) Evaluation of Technical Feasibility of Reusing Coal Ash in Dense Asphalt Mixes by Assessing Mechanical Performance. An Acad Bras Cienc 93:. <https://doi.org/10.1590/0001-3765202120201662>
97. Durga Priyanka B, Kumar PVA, Dedeepya K, et al (2014) Use of Fly Ash as Mineral Filler for Bituminous Paving Mixes. IJRET: International Journal of Research in Engineering and Technology 4:56–60